Terrain Fabrics, by Doshi Levien

kettal

Terrain Fabrics

100% Solution-dyed Acrylic — 400g/m2

This is a range of premium fabrics for indoor and outdoor furniture.

The hydrophobic technology applied works by impeding the liquids that permeate the fabric, forcing them to roll out of the fabric in the form of drops. The fabric protection that brings out the liquids allows for drops of water and oil to be eliminated during normal washing without leaving any traces.

leaving any traces.
Solution-dyed acrylic; is dyed before thread is created. A liquid acrylic solution is mixed with dye and then formed into a fiber and spun on thread.










Anti-mould


UV-Resistant

NFPA 260

CAL 117



Thermal welding in all stitching applied



Air circulate system



Water repelent



Laminated



kettal

Terrain Fabrics

Material	100% acrylic, dyed	100% acrylic, dyed	
Roll width	160 cm		
Grammage	400 g/m2	ISO 2286-2	
Resistant to superficial wetting	100 ISO 24920	ISO 24920	
Oil resistance	6	AATCC 118	
Colour fastness to artificial weathering	7-8 blue scale (8)	ISO 105-B04	
Colour fastness to light	7-8 blue scale (8)	ISO 105-B02	
Title warp and weft	Nm 2/34 Nm 6/34		
Tensile strength, warp	180 daN/5 cm	ISO 13934	
Tensile strength, weft	240 daN/5 cm	ISO 13934	
Tear resistance, warp	21.0 daN	ISO 4674-1	
Tear resistance, weft	29.0 daN	ISO 4674-1	
Abrasion resistance (Martindale)	30,000 cycles	ISO 12947-2	
Abrasion resistance (Wyzenbeek)	15,000 double rubs	ASTM D4157	
Cigarette ignition classification	Class 1	NFPA 260	
Material resistance to ignition without flame	Pass	CA TB 117	



kettal

Sandstone

Coral

309

Terrain Fabrics

Certificates



Maintenance

Kettal cushions have received an exclusive treatment with fluorocarbon to protect the fabric from possible stains or other liquids. It can be brushed, washed with water and neutral PH soap without problem, due to its mass tinting. After certain time, the fabric looses the fluorocarbon protect property; to reactivate it, we recommend to iron the fabric.





30% Bleach / 70% Water

Ironing reactivates the finish