


Wood

kettal

Description

Wood material is used exclusively on A collection's chair and tables. This Wood finishes collection is composed by Natural and Burnt Ash and Oak.





Suitable for indoor use only



Technical specifications

Grain	Straight / medium size
Texture	Slightly sanded surface
Monnin Hardness	5.1 (Oak) / 4.2 (Ash)
Coeff. volumetric shrinkage	0,43% (Oak) / 13,4% (Ash)
Total tangential shrinkage	10,5% (Oak) / 7,8% (Ash)
Total radial shrinkage	5,6% (Oak) / 4,8% (Ash)
TS/RS ratio	1,9 / 1,6
Strength (Compressive)	Perpendicular / Parallel (Oak: 7.8 / 43 MPa; Ash: 10.8 / 51 MPa)
Modulus of elasticity	Between 6670 - 16000 MPa (Oak) / 12000 MPa (Ash)

Colour Options



Natural OakBurnt Oak



Natural AshBurnt Ash

